


## Technical data sheet

# DELTA-MULTI-BAND®

Universal, highly age-resistant adhesive tape with maximum adhesive strength for exterior and interior applications.



Characteristics	Methods	Values/Description
<b>Description</b>		
<b>Application</b>	–	Universal, highly age-resistant adhesive tape with maximum adhesive strength for outdoor and indoor use. Also suitable for bonding the overlaps of DELTA®-RADONSTOP in applications above the floor slab (Versions M 100 and M 150).
<b>Material</b>	–	Solvent-free and plasticiser-free pure acrylic adhesive of medium viscosity with embedded diagonal PET scrim on UV-stabilised white PE cover film with siliconised backing paper.
<b>Special features</b>	–	In accordance with DIN 4108-7 and DIN 4108-11 (BoPET, beech and DELTA®-Membranes) <ul style="list-style-type: none"> <li>• Static peel test (90°) 24 h load duration: pass</li> <li>• Dynamic peel test (180°) initial and after ageing: pass</li> </ul> Complies with DTU 31.2 (F), SIA 180, SIA 232/1 (CH), ÖNORM B 8110-2 (A), ÖNORM B 2340
<b>Characteristics</b>		
<b>Fields of application</b>	–	For bonding and repairing all DELTA® films (in each case on the printed upper side of the film) as well as bonding to all comparable substrates and those made of plastic (hard), metal, smooth wood and wood-based materials. Bonding to rough wood and mineral substrates or similar is not recommended or only recommended to a limited extent. Not suitable for regenerated films and films with chlorinated kerosene additives or for use in saunas and swimming pools.
<b>Data</b>		
<b>Total thickness (without release paper)</b>	–	approx. 0,3 mm
<b>Peel strength on DELTA®-REFLEX</b>	EN 12316-2	≥ 30 N/50 mm
<b>Shear strength</b>	EN 12317-2	≥ 50 N/50 mm
<b>S<sub>d</sub> value</b>	EN 1931	approx. 35 m
<b>UV resistance</b>	–	12 month
<b>Radon diffusion coefficient</b>	–	< 1,0 · 10 <sup>-11</sup> m²/s
<b>Roll width</b>	–	60 mm / 100 mm* / 150 mm* (* with split release paper)
<b>Roll length</b>	–	25 m
<b>Functional temperature range</b>	–	-40 °C to +80 °C
<b>Storing</b>	–	+5 °C to +30 °C (before processing tempered storing recommended)
<b>Processing (ambient and component temperature)</b>	–	from -5 °C
<b>Packaging Unit</b>	–	DELTA-MULTI-BAND® M 60: 10 rolls/box – 85 boxes/pallet DELTA-MULTI-BAND® M 100: 6 rolls/box – 85 boxes/palle DELTA-MULTI-BAND® M 150: 4 rolls/box – 85 boxes/pallet
<b>Additional information</b>		
<b>Substrate requirements / pre-treatment</b>	–	Films and substrates must be stable, dry, free from frost, dust, dirt and grease, sufficiently stable, free from plasticizers, free from ice and hoar frost and free from substances that repel adhesives. Substrates that are not sufficiently stable, e.g. sanding substrates, should be treated with DELTA®-HF PRIMER. The surface tension of the substrate should be above 36 mN/m.

Processing notes and conditions for application	–	<ul style="list-style-type: none"><li>• A test bonding on site is recommended.</li><li>• Membranes to be bonded must be laid and fastened without tension or wrinkles.</li><li>• The overlaps must be bonded without gaps, i. e. without folds or voids.</li><li>• The adhesive strength depends on the storage, substrate and ambient conditions as well as on the time. The final strength builds up slowly.</li><li>• Store the adhesive tape at a controlled temperature before use (not in frosty conditions).</li><li>• The adhesive tape must be applied to the substrates to be bonded without tension and without shearing or peeling stress. It must be ensured that no stresses occur even after bonding, e.g. by installing battens under vapor barriers to prevent sagging.</li><li>• The construction process must be coordinated in such a way that humidity levels &gt; 80 % RH are avoided during and after bonding.</li><li>• The adhesive is not permanently UV-resistant and must be covered and protected from UV light no later than 12 months after application.</li></ul>
Classification of waste (2014/955/EU)	–	08 04 10

The content of this data sheet describes the current state of knowledge at the time of publication and make no claim to be complete. The information listed does not release from self-dependent behaviour. With publication of this sheet all previous versions are not valid any longer. Errors and typing errors reserved.

