

Technical data sheet

DELTA-XX PLUS® LIGHT

Durable, universally applicable, diffusion-open multi-layer underlay and sarking membrane for the protection of pitched roofs with roofing against moisture and harmful environmental influences.



Characteristics	Methods	Values/Description
Description		
Application	–	For fully insulated pitched roofs without formwork. Corresponds to the ZVDH product data sheet UDB/USB. Also suitable for temporary coverings and as a façade membrane behind ventilated claddings with closed joints.
Material	–	Multi-layer, pitched roof membrane made of a tear-resistant, diffusion-open combination of PP spunbonded fleece and PU functional film. With integrated self-adhesive edges.
Weight	EN 1849-2	approx. 130 g/m²
Thickness	–	approx. 0.5 mm
Straightness (≤ 30 mm / 10 m)	EN 1848-2	passed
Watertightness		
Resistance to water penetration before and after ageing (336 h UV)	EN 1928	W1
Watertightness after long-term exposure (448 d at 5±2 m/s; 70 °C)	EAD 030218-01-0402	W1
Driving rain test	Test University of Berlin	watertight
Water vapour transmission		
S_d-value	EN ISO 12572	approx. 0.08 m
Diffusion resistance factor μ	–	approx. 160
Water vapour transmission	EN ISO 12572	approx. 2.17 · 10 ⁻⁹ kg/m² · s · Pa
Mechanical properties		
Tensile strength MD/CD	EN 12311-1	approx. 270/220 N/5 cm
Tensile strength after ageing (336 h UV) MD/CD	EN 12311-1	approx. 270/220 N/5 cm
Elongation at break MD/CD	EN 12311-1	approx. 80 % / 80 %
Tear resistance MD/CD	EN 12310-1	approx. 170/180 N
Dimensional stability	EN 1107-2	<1.0 %
Flexibility at low temperature	EN 1109	-45 °C
Miscellaneous characteristics		
Fire resistance	EN 13501-1	E
Fire code number	VKF	5.2
Air permeability	EN 12114	< 0.1 m³/h · m²
Service temperature range	–	-40 °C bis +80 °C
Short-term maximum temperature load of the material (< 8 h/day)	–	+100 °C
UV-related outdoor exposure time	–	8 weeks
Temporary roofing function	–	4 weeks
Density	–	approx. 260 kg/m³
Thermal conductivity	–	approx. 0.17 W/m · K
Specific heat capacity c	–	approx. 1,000 J/kg · K
Dimension	–	50 m × 1.50 m
Weight of one roll	–	approx. 9.75 kg
Packaging unit	–	24 rolls/pallet
CE-conformity	EAD 030218-01-0402, EN 13859-1 +2	yes
Certificates	–	UDB/USB in accordance to ZVDH rules. Increased ageing requirement: passed, ZVDH-Product data sheet, table 1 European Technical Assessment ETA-22/0389 (service life ≥ 25 years)
External test reports	–	2,000 h QUV

The content of this data sheet describes the current state of knowledge at the time of publication and make no claim to be complete. The information listed does not release from self-dependent behaviour. With publication of this sheet all previous versions are not valid any longer. Errors and typing errors reserved.



Accessories

• DELTA-MULTI-BAND® FLEXX:

Universal, highly age-resistant adhesive tape with maximum adhesive strength for outdoor and indoor use. For sealing and repairing all DELTA® sheets (applied to the printed upper side) as well as to join them to any similar surfaces and surfaces made of plastic (rigid), metal, smooth wood, and wood-based materials. Particularly suitable for bonding of non-woven surfaces (e.g. DELTA-XX PLUS®, DELTA®-PVG PLUS).

Material: special reinforced UV-stabilized black polyethylene (PE) film and highly aggressive solvent-free acrylic adhesive with an easily removed paper release liner. Meets the requirements of the norm DIN 4108-11.

Dimension: 60 mm × 25 m / 60 mm × 40 m / 100 mm × 25 m* (*with slit paper release liner)

• DELTA-MULTI-BAND®:

Single-sided high-performance adhesive tape to seal and repair all DELTA® sheets (applied to the printed upper side) as well as to join them to any similar surfaces and surfaces made of plastic (rigid), metal, smooth wood, and wood-based materials. Suitable for inside and outside application.

Material: special reinforced UV-stabilized polyethylene (PE) film and highly aggressive solvent-free acrylic adhesive with an easily removed paper release liner. Meets the requirements of the norm DIN 4108-11.

Dimension: 60 mm / 100 mm* / 150 mm* (*with slit paper release liner).

• DELTA®-FLEXX-BAND FG 80 / FG 150:

Sealing and connecting tape suitable for outside and inside details such as skylights, flue pipes, cables. Thickness approx. 2 mm.

Material: solvent-free butyl rubber adhesive on special PE film with siliconized PE cover foil, slit in the middle.

Dimension: 6 m × 80 mm / 10 m × 150 mm.

Also available as DELTA®-FLEXX BAND F 100 with geotextile surface: 10 m × 100 mm.

• DELTA®-TILAXX ULTRA:

Universally applicable, permanently elastic as well as solvent-free cartridge hybrid adhesive based on MS polymers (modified silanes) for bonding overlaps of all DELTA® membranes, as well as their connections to masonry, concrete, wood, derived timber products, aluminium, steel, rigid PVC and bitumen.

Filling weight: 290 ml

• DELTA®-THAN:

Permanently elastic cartridge adhesive made of special rubber for outside application, for bonding and joining DELTA® membranes.

Filling weight: 310 ml per cartridge / 600 ml per tubular bag.

Consumption: approx. 7 running metres / cartridge or 14 running metres / tubular bag

• DELTA®-SCHAUM-BAND:

VPE foam nail-sealing tape off the roll. For sealing nail penetrations. Single-faced. Apply to sheet surfaces or counterbattens.

Dimension: 40 mm × 30 m (DELTA®-SB 40) / 50 mm × 30 m (DELTA®-SB 50) / 60 mm × 30 m (DELTA®-SB 60) / 70 mm × 30 m (DELTA®-SB 70) / 80 mm × 30 m (DELTA®-SB 80)

• DELTA®-HF PRIMER:

Solvent-free adhesion primer for porous substrates. Serves to significantly improve the adhesion properties of surfaces to be bonded, e.g. wood fibre boards, sanding masonry and concrete. Also suitable for preparing the surface of DELTA-XX PLUS® types before bonding DELTA®-FLEXX-BAND.

Drying time: approx. 15 to 60 min.

Filling weight: 1,000 g bottle.

Consumption: Strongly dependent on the absorbency of the substrate. Ex. stone / concrete: approx. 12 m²/1,000 g; Ex. wood fibre boards: approx. 6 m²/1,000 g